

1,65 Kg/l **APPLICATION:** Brush, roller, spray

**DILUTION:** 20%-30% by volume with water 30%-40% by volume with water for spray applications

SPECIFIC WEIGHT:


YIELD: 10-14 m<sup>2</sup>/l per coat depending on the substrate's absorption rate **MINIMUM APPLICATION TEMPERATURE:** +10°C

**AVAILABLE IN ANY COLOUR** 

**AVAILABLE IN ANY COLOUR** 

Water-based matte enamel

1



**TYPES OF SUBSTRATE:** Newly applied gypsum plaster finishes, plasterboard, and old washable and breathable paints that are still well anchored. Also suitable for industrial buildings with prefabricated concrete walls and ceilings.

Brush, roller, spray **DILUTION:** 20%-30% by volume with water 30%-40% by volume with water for spray applications

+10°C

**APPLICATION:** 

1,7 Kg/l

SPECIFIC WEIGHT:

YIELD: 10-14 m<sup>2</sup>/l per coat depending on the substrate's absorption rate

**MINIMUM APPLICATION TEMPERATURE:** 

2

AMBRO MAT

TYPES OF SUBSTRATE: Newly applied gypsum plaster finishes, plasterboard, and old washable and breathable paints that are still well anchored, after applying a primer.

Water-based wall enamel paint for interior use. Smooth, matte finish. Good yield and coverage. Excellent washability. Unsaponifiable and odourless.

SPECIFIC WEIGHT: 1,36 Kg/l

**DILUTION:** 20%-30% by volume with water 30%-40% by volume with water for spray applications

10-14 m<sup>2</sup>/l per coat depending on the substrate's

3

**APPLICATION:** Brush, roller, spray

YIELD:

absorption rate

MINIMUM APPLICATION TEMPERATURE: +10°C

**AMBRO SAT** 

**TYPES OF SUBSTRATE:** Newly applied gypsum plaster finishes, plasterboard,

and old washable and breathable paints that are still

œ

Quartz coating

well anchored, after applying a primer.

SPECIFIC WEIGHT:

**APPLICATION:** 

1,36 Kg/l

+10°C

Water-based wall enamel paint for interior use. Smooth, satin finish. Good yield and coverage. Excellent washability. Unsaponifiable and odourless.

**AVAILABLE IN ANY COLOU** Brush, roller, spray **DILUTION:** 

30%-40% by volume with water for spray applications

YIELD: 10-14 m<sup>2</sup>/l per coat depending on the substrate's absorption rate

**MINIMUM APPLICATION TEMPERATURE:** 

4

Waterborne, quartz flour-based paint for exterior use.

Newly applied gypsum plaster finishes and old paints

20%-30% by volume with water

MILANO **MAIAQUARZ** 

**TYPES OF SUBSTRATE:** 

that are still well anchored.

SPECIFIC WEIGHT:

**APPLICATION:** 

20%-30% by volume with water

1,65 Kg/l

YIELD: 8-10 m<sup>2</sup> per coat

+5 °C, +40 °C

Brush, roller **DILUTION:** 

5

TOMMY Acrylic-siloxane coating

High-thickness fibre-reinforced acrylic-siloxane coating for external walls. Containing anti-mould and anti-algae

**MINIMUM APPLICATION TEMPERATURE:** 

TYPES OF SUBSTRATE: Newly applied gypsum plaster finishes and old paints that are still well anchored. Particularly suitable for EIFS systems.

Steel trowel and subsequently plastic trowel for

Available in different grain sizes (1.2-1.5).

additives for good durability.

**SPECIFIC WEIGHT:** 

**APPLICATION:** 

smoothing

**DILUTION:** Ready for use

+5 °C, +40 °C

1,80 Kg/l

**AVAILABLE IN ANY COLOUR** YIELD: 2-2.5 Kg/m<sup>2</sup> depending on the grain size MINIMUM APPLICATION TEMPERATURE:

6

Via Leonardo da Vinci, 172 Follow us on social media TREZZANO SUL NAVIGLIO (MI) **ITALY** (o) **f** Tel. +39 02 44576411









